



DECKING - HARDWOOD MASSARANDUBA

AVAILABLE GRADES:-

Select
Colour dark reddish brown which will grey
on exposure to weathering

PROPERTIES

BOTANICAL NAME	<i>Manilkara bidentata</i>
PHYSICAL/STRUCTURAL PROPERTIES	Strong, heavy and very hard
MOISTURE CONTENT	Shipping dry - 25% average
TYPICAL APPLICATIONS	Decking, heavy construction, boat frames, bridges and flooring
DENSITY	1050kg/m ³
WASTAGE ALLOWANCE	10 -15% length waste
ORIGIN	South America
DURABILITY	Durable to very durable 50 years plus
ENVIRONMENTAL CREDENTIALS	FSC
STORAGE ADVICE	Undercover to avoid colour change with weathering prior to installation
SUPPLIED FINISH	Machined to profile
WORKING PROPERTIES	Moderately easy to work despite its high density, it machines and finishes to a very smooth surface
STABILITY	Fairly stable once seasoned, although slight tendency to bow

HARDWOOD DECKING MASSARANDUBA				
Product	Profile	Code	Available ex-Stock	Environmental Credentials
21 x 145mm x 2m - 4.8m	Reversible Deck board	H0003752	Y	FSC
28 x 145mm x 2m - 4.8m	Reversible Deck board	H0003753	Y	FSC
28 x 145mm x 2m - 4.8m	Smooth, rounded 4 corners Deck board	H0006114	Y	FSC

Additional specifications, sizes, chain of custody and specials are available to order



Reversible Decking Board



Smooth Rounded 4 Corners Deck Board

