



TEMPERATE HARDWOODS WALNUT - AMERICAN BLACK

GRADE OVERVIEW:-

FAS, FAS/FAS IF, No.1 Common, No.2 Common.

PROPERTIES

BOTANICAL NAME	<i>Juglans nigra</i>
DENSITY	660 kg/m ³
DISTRIBUTION	Black walnut is widely distributed throughout North America from south Ontario southward to Texas, and in the east from Maine to Florida, but it is not plentiful, firstly because its growth is scattered, and secondly, because of the clearing of ground for cultivation and the demands for the timber have exhausted the supply in many areas
DRYING	Dries rather slowly with a tendency to honeycombing
DURABILITY	Moderately durable
ENVIRONMENTAL CREDENTIALS	FSC available
MOISTURE CONTENT	6% - 8% (+/-2%)
ORIGIN	North America
PHYSICAL/STRUCTURAL PROPERTIES	Walnut is a tough, hard timber of medium density with moderate bending and crushing strengths and low stiffness. Good steam bending classification
PURCHASING CYCLE	12 month
STORAGE ADVICE	Under cover
TYPICAL APPLICATIONS	Furniture, cabinet making, architectural interiors, high class joinery, doors, flooring, gunstocks and panelling. A favoured wood for using in contrast with lighter coloured timber
WORKING QUALITIES	Walnut works easily with hand and machine tools and nails. Screws and glues well. Holds paint and stain very well and can be polished to an exceptional finish. Performs best when dried slowly and has good dimensional stability

WALNUT - AMERICAN BLACK			
Product	Code	Stocked	Environmental Credentials
KD FAS/FAS1F			
1"	H0000155	Y	✓
1 x 10"+	H0005008	Y	✓
1.25"	H0000314	Y	✓
1.5"	H0000156	Y	✓
2"	H0000196	Y	✓
2.5"	H0000157	Y	✓
3"	H0000198	Y	✓
KD FAS/FAS1F FSC			
1"	H0004032	Y	FSC
2"	H0004033	Y	FSC
KD FAS/FAS1F RTW - Ripped to width			
1 x 3.5"	H0005678	Y	✓
1 x 4.5"	H0005679	Y	✓
FAS/FAS1F PTW - Pulled to Width			
1 x 6"	H0005890	Y	✓

Additional specifications, sizes, chain of custody and specials are available to order

