

American White Ash

BOTANICAL NAME

Fraxinus spp



OVERVIEW

FAS, FAS/FAS IF, No.1 Common, No.2 Common. Ash can also be purchased with colour selection such as W1F (white 1 face).

Further Product Information

APPLICATIONS & USES

Furniture, flooring, doors, architectural interiors, high class joinery and mouldings, kitchen cabinets, panelling, tool handles. A versatile good looking wood offering great value plus wide range of joinery and furniture applications

DIMENSIONS

KD FAS/FAS1F (Ash American White Kiln Dried)

- **1**"
- $-1 \times 8" +$
- 1 x 13"+
- -1.25"
- 1.25 x 8"+
- 1.25 x 13"+
- 1.5"
- 1.5 x 8"+
- 1.5 x 13"+
- **− 2**"
- $-2 \times 8" +$



$-2 \times 13"+$
- 2.5"
-3"
-4 "
KD FAS/FAS1F FSC (Ash – American White Kiln Dried)
- 1"
- 1.25"
- 1.5"
- 2"
- 2.5"
- 3 "
- 4"
VD FACIFACAF MAF (Act. American Milita Vila Duical)
KD FAS/FAS1F W1F (Ash – American White Kiln Dried)
- 1"
KD Prime – RTW (Ripped to width) (Ash – American White Kiln Dried)
– 1 x 3"
- 1 x 4"
– 1 x 5"
- 1 x 6"
-1 x 7"
ENVIRONMENTAL CREDENTIALS
Certification
FSC
FSC CW
Origin
North America
Notifi America
TECHNICAL INFORMATION
Density
670 kg/m3 (Density can vary by 20% or more)
2. 2. 1.g
Discosing Comments and
Physical Structure
Properties Sapwood is light in colour with heartwood varying from light brown to darkish red



Durability

Not durable

Drying

Dries with little distortion

Moisture Content

8 - 10% (+/-2%)

Working Qualities

Ash machines well, is good in nailing, screwing and gluing as well as being stained and polished to a very good finish. Good stability means little movement in Performance

Storage Advice

Under cover

Purchasing Cycle

12 month